

ID	From (m)	To (m)	Length (m)	Li2O (%)	Ta2O5 (ppm)
MR-23-01	40	65	25	2	228
MR-23-01	43	52	10	3	202
MR-23-02	9	35	26	3	268
MR-23-02	9	23	14	3	268
MR-23-03	23	30	6	1	227
MR-23-04	28	30	3	1	141
MR-23-05	6	46	40	1	87
MR-23-05	6	16	10	1	99
MR-23-06	18	55	37	1	93
MR-23-06	43	48	6	2	135
MR-23-07	22	73	51	1	105
MR-23-07	31	43	13	2	192
MR-23-08	11	13	2	0	112
MR-23-09	66	77	11	1	69
MR-23-10	39	87	48	1	80
MR-23-10	79	87	8	2	73
MR-23-10	79	87	8	2	73
MR-23-10	79	87	8	2	73
MR-23-10	79	87	8	2	73
MR-23-11	84	119	35	1	117
MR-23-11	99	106	7	2	136
MR-23-12	92	133	41	1	94
MR-23-12	103	109	6	2	169
MR-23-13	25	36	10	1	171
MR-23-14	47	63	16	3	98
MR-23-14	53	62	10	3	113
MR-23-15	90	106	16	2	49
MR-23-16	96	109	13	3	86
MR-23-17	75	90	15	2	69
MR-23-18	88	100	12	2	117
MR-23-19	68	82	14	3	70
MR-23-20	77	84	8	2	97
MR-23-21	71	73	2	2	83
MR-23-25	45	54	9	3	77
MR-23-26	50	60	11	3	166
MR-23-27	108	114	6	0	169
MR-23-28	4	41	37	2	154
MR-23-29	3	35	32	2	168
MR-23-30	2	26	25	2	143
MR-23-31	15	16	1	1	298
MR-23-31	28	34	5	1	321
MR-23-31	42	47	4	1	198
MR-23-31	54	56	2	1	314

ID	From (m)	To (m)	Length (m)	Li2O (%)	Ta2O5 (ppm)
MR-23-32	27	36	8	1	173
MR-23-32	43	46	3	2	260
MR-23-32	53	56	3	0	233
MR-23-33	140	144	4	2	243
MR-23-33	159	162	3	1	206
MR-23-33	164	165	1	0	348
MR-23-33	170	171	1	1	847
MR-23-33	186	189	3	1	305
MR-23-33	191	192	1	1	352
MR-23-33	197	204	7	1	316
MR-23-33	218	220	2	2	235
MR-23-33	232	235	3	1	250
MR-23-34	77	79	3	2	245
MR-23-35	35	46	12	1	90
MR-23-36	39	42	4	1	272
MR-23-36	176	178	2	1	298
MR-23-36	226	235	9	1	149
MR-24-38	72	72	1	1	150
MR-24-39	19	23	4	1	184
MR-24-39	52	58	6	1	146
MR-24-39	128	131	3	1	232
MR-24-40	10	11	1	1	145
MR-24-40	78	84	6	1	207
MR-24-41	127	127	0	3	283
MR-24-43	10	28	19	1	81
MR-24-43	84	87	3	1	101
MR-24-44B	14	31	17	1	79
MR-24-45	119	133	14	1	96
MR-24-45	161	163	2	1	171
MR-24-46	35	52	17	1	97
MR-24-47	144	145	1	1	143
MR-24-47	200	209	9	1	146
MR-24-47	236	239	3	1	143
MR-24-47	275	278	4	1	105
MR-24-48	43	62	19	1	93
MR-24-49	7	65	58	2	142
MR-24-49	70	72	2	1	122
MR-24-50	8	36	28	1	148
MR-24-50	51	53	2	1	151
MR-24-51	109	113	4	2	174
MR-24-51	120	123	3	1	200
MR-24-51	145	149	5	1	122
MR-24-53	225	227	2	1	143

ID	From (m)	To (m)	Length (m)	Li2O (%)	Ta2O5 (ppm)
MR-24-53	251	274	23	0	95
MR-24-54	67	71	5	1	198
MR-24-55	68	79	12	1	166
MR-24-56	49	59	10	0	44
MR-24-57	54	61	7	1	88
MR-24-58	90	91	1	1	109
MR-24-58	261	262	1	1	269
MR-24-59	153	155	2	2	273
MR-24-59	172	177	5	1	213
MR-24-59	246	251	5	2	195
MR-24-59	256	259	3	1	132
MR-24-59	299	300	2	1	177
MR-24-59	308	311	3	1	166
MR-24-59	314	341	27	1	93
MR-24-60	18	36	18	1	189
MR-24-60	39	51	12	1	154
MR-24-60	67	67	1	1	271
MR-24-60	76	88	12	1	154
MR-24-60	93	125	32	2	240
MR-24-60	145	147	2	0	219
MR-24-60	183	184	1	1	209
MR-24-60	326	327	1	1	274
MR-24-60	342	344	2	1	139
MR-24-61	7	76	69	2	147
MR-24-62	6	100	93	2	160
MR-24-64	55	78	23	0	223
MR-24-65	44	78	34	1	125
MR-24-66	146	165	19	1	127
MR-24-66	191	191	0	2	234
MR-24-66	235	236	1	1	275
MR-24-66	253	260	7	1	173
MR-24-66	282	283	1	1	317
MR-24-67	32	35	3	0	308
MR-24-69	58	70	12	0	184
MR-24-72	3	5	2	1	223
MR-24-72	22	37	16	1	255
MR-24-72	44	49	5	2	197
MR-24-72	56	58	2	2	281
MR-24-72	61	61	1	2	272
MR-24-72	62	66	3	2	211
MR-24-72	70	82	12	2	167
MR-24-72	114	132	18	1	110
MR-24-72	154	158	4	1	131

ID	From (m)	To (m)	Length (m)	Li2O (%)	Ta2O5 (ppm)
MR-24-73	88	129	40	2	154
MR-24-73	165	172	7	1	154
MR-24-74	111	135	24	1	125
MR-24-75	22	24	2	1	190
MR-24-75	79	82	3	1	236
MR-24-75	132	138	6	2	133
MR-24-75	219	220	1	0	88
MR-24-75	227	240	13	1	94
MR-24-75	246	246	0	1	565
MR-24-75	250	250	0	1	249
MR-24-75	253	254	2	2	441
MR-24-75	259	260	1	1	306
MR-24-75	264	269	5	2	277
MR-24-76	57	59	2	2	233
MR-24-76	84	86	2	2	439
MR-24-76	88	92	4	2	398
MR-24-76	125	151	26	1	328
MR-24-76	163	164	2	2	263
MR-24-76	179	205	26	1	248
MR-24-76	216	221	5	1	232
MR-24-76	258	261	3	1	240
MR-24-76	295	317	22	2	492
MR-24-77	60	62	2	0	669
MR-24-78	49	52	3	2	670
MR-24-78	73	86	13	1	233
MR-24-78	104	110	6	1	189
MR-24-78	140	146	7	1	229
MR-24-78	153	153	0	2	72
MR-24-78	179	180	2	1	209
MR-24-78	246	246	1	1	288
MR-24-78	272	279	8	2	234
MR-24-78	294	304	10	2	221
MR-24-78	310	310	1	1	99
MR-24-78	316	321	6	2	144
MR-24-80	114	120	6	1	237
MR-24-80	147	150	3	1	184
MR-24-80	158	174	16	1	189
MR-24-80	160	163	3	2	264
MR-24-80	182	185	3	1	326
MR-24-81	71	77	7	1	155
MR-24-81	83	89	7	1	210
MR-24-81	186	188	2	1	162
MR-24-81	213	223	10	1	153

ID	From (m)	To (m)	Length (m)	Li2O (%)	Ta2O5 (ppm)
MR-24-82	4	4	0	1	204
MR-24-82	167	170	4	1	195
MR-24-83	161	162	0	0	513
MR-24-83	174	174	1	1	193
MR-24-84	20	22	-1	0	314
MR-24-84	158	160	-1	1	119
MR-24-84	179	198	-1	2	149
MR-24-84	180	186	-1	3	162
MR-24-85	20	20	0	0	457
MR-24-85	33	34	0	0	364
MR-24-85	63	64	1	0	305
MR-24-85	72	77	4	1	286
MR-24-85	80	82	3	1	157
MR-24-85	141	142	1	0	255
MR-24-85	150	151	2	1	251
MR-24-85	152	153	1	1	212
MR-24-85	168	178	10	2	249
MR-24-85	185	188	3	1	246
MR-24-86	161	163	1	0	812
MR-24-86	167	170	3	2	152
MR-24-86	173	175	2	1	70
MR-24-86	237	237	0	0	2253
MR-24-87	138	143	5	1	105
MR-24-87	149	186	37	1	63
MR-24-87	157	163	6	2	70
MR-24-87	192	196	4	2	92
MR-24-87	201	202	1	1	175
MR-24-89	100	123	23	1	87
MR-24-90	43	54	11	2	57
MR-24-91	45	101	56	1	130
MR-24-91	69	76	7	2	161
MR-24-92	73	87	14	3	52
MR-24-93	82	92	10	2	80
MR-24-94	4	20	16	1	75
MR-24-94	4	11	6	2	116
MR-24-94	13	14	2	1	41
MR-24-94	16	20	4	1	73
MR-24-94	35	36	1	0	150
MR-23-32	144	146	2	2	258
MR-23-32	148	150	2	1	287
MR-23-32	158	166	8	1	169
MR-25-95	50	57	7	1	111
MR-25-95	124	132	8	1	99

ID	From (m)	To (m)	Length (m)	Li2O (%)	Ta2O5 (ppm)
MR-25-95	225	228	3	2	310
MR-25-95	290	291	1	1	113
MR-25-95	299	301	2	1	252
MR-25-95	304	307	4	1	84
MR-25-96	56	68	12	1	321
MR-25-96	148	151	3	1	197
MR-25-96	161	163	3	0	211
MR-25-97	18	23	5	1	182
MR-25-98	176	183	7	1	138
MR-25-101	173	201	28	1	125
MR-25-102	17	21	4	1	143
MR-25-102	66	69	3	3	148
MR-25-102	96	106	9	1	64
MR-25-102	118	120	2	1	191
MR-25-102	133	135	2	2	159
MR-25-102	139	140	1	1	118
MR-25-102	158	160	2	1	384
MR-25-102	167	202	36	2	184
MR-25-102	212	215	3	1	130
MR-25-102	240	244	4	1	144
MR-25-102	248	251	3	2	237
MR-25-102	255	257	2	2	172
MR-25-102	292	296	4	2	124
MR-25-102	299	305	6	1	65
MR-25-105	36.7	38.4	1.7	1.4	287
MR-25-105	43.1	44.3	1.2	1.5	145
MR-25-105	77.5	90	12.5	1.4	254
MR-25-105	154.75	156.15	1.4	2.2	253
MR-25-105	161.6	162.6	1.0	1.1	206
MR-25-105	203.25	206	2.8	0.9	239
MR-25-105	228.8	231.25	2.5	0.9	239
MR-25-105	236.25	238.3	2.1	1.5	221
MR-25-105	241.95	247.65	5.7	0.7	225
MR-25-105	251.8	253.7	1.9	1.0	176
MR-25-105	261.15	269.4	8.3	0.9	129
MR-25-105	273.7	282.7	9.0	1.0	204
MR-25-105	287.35	288.5	1.2	1.2	239
MR-25-105	325.1	326.25	1.2	1.3	107
MR-25-106	45.5	62.9	17.4	1.0	166
MR-25-106	123.05	124.8	1.8	0.5	154
MR-25-106	128.2	134.15	6.0	1.3	312
MR-25-106	141.8	147.6	5.8	1.3	227
MR-25-106	157.7	162.3	4.6	1.3	233

ID	From (m)	To (m)	Length (m)	Li2O (%)	Ta2O5 (ppm)
MR-25-106	236.85	241.2	4.4	2.0	197
MR-25-106	256.3	257.55	1.3	0.8	157
MR-25-106	283.45	284.65	1.2	1.1	232
MR-25-107	23.8	28.8	5.0	1.4	202
MR-25-108	26.8	31.9	5.1	1.0	169
MR-25-108	82.75	84.9	2.2	1.0	208
MR-25-108	96	98.4	2.4	1.2	162
MR-25-108	104.4	106.85	2.5	0.7	178
MR-25-108	118.7	120.6	1.9	1.0	192
MR-25-108	128.75	131.75	3.0	0.9	201
MR-25-108	135.8	138	2.2	1.6	214
MR-25-108	163.1	170.2	7.1	1.2	199
MR-25-108	253	255.2	2.2	1.6	352
MR-25-109	21.4	34.7	13.3	1.3	351
MR-25-109	64.5	69.15	4.7	1.2	266
MR-25-109	106.6	111.75	5.2	1.3	222
MR-25-110	42.6	47.6	5.0	1.0	245
MR-25-110	217.8	251	33.2	1.1	128
MR-25-111	61.8	64.05	2.3	1.1	172
MR-25-115	92.6	121.85	29.3	1.2	179
MR-25-112	113.9	116.25	2.3	1.4	183
MR-25-112	251.45	253.65	2.2	0.8	172
MR-25-112	316	321.4	5.4	1.2	193
MR-25-112	328	339	11.0	1.2	160
MR-25-112	367.85	387.8	20.0	1.3	231
MR-25-116	52.55	55.75	3.2	0.9	172
MR-25-116	74.5	76.75	2.3	0.5	140
MR-25-116	151.95	164.9	13.0	0.3	123
MR-25-116	200.7	203.55	2.9	1.1	141
MR-25-117	210.9	212.9	2.0	1.2	281
MR-25-117	341.45	344.6	3.2	1.8	309
MR-25-118	3.95	9	5.1	1.4	429
MR-25-119	3.35	35.9	32.6	1.3	129
MR-25-120	38.25	53.8	15.6	2.6	143
MR-TR-25-01	0	26	26.0	2.5	150
MR-TR-25-02	0	21	21.0	1.8	81
MR-TR-25-03	0	10	10.0	0.7	122
MR-TR-25-04	0	4	4.0	1.6	158